

# PRODUCT DATA SHEET

## ECOFOAM RWF



### Developed for

### Polyol

### Isocyanate

### Product description

Spray foam (B2), solely water blown

Mixture of polyether polyols, polyester polyols, flame retardant, activators (contains amine), stabilizer and water

Product based on Diphenylmethanediisocyanate (MDI)

### Formulation

### Typical properties

		Polyol	Isocyanate
Density 25°C	g/cm <sup>3</sup>	ca. 1,15	ca. 1,23
Viscosity 25°C	mPas	ca. 400	ca. 200

A-component	ECOFOAM RWF	100 Parts by weight
B-component	Pur'fect 100	107 Parts by weight

<b>Ratio</b>	<b>A-comp. : B-comp.</b>	<b>100:100 parts by volume</b>
		<b>100:107 parts by weight</b>

### Cup test

Material temperature		20°C
Cup weight		
A-component		30 g
B-component		32 g
Parameter		
Cream time		ca. 4 sec
Gel time		ca. 11 sec.
Free rise density		ca. 33 kg/m <sup>3</sup>

### Safety

Please pay attention to the safety data sheet.  
It contains handling information.

It is advisable to avoid direct skin contact with freshly produced polyurethane, because of the fact that in case of not covered polyurethane the surface may obtain traces of starting and successive products which are e.g. dangerous to health or have irritating, cauterizing and/or sensitizing properties.

PRODUCT DATA SHEET  
**ECOFOAM RWF**



---

<b>Storage</b>	<b>Storage, packaging and supplying</b> The packaging has to be closed very well. This product is very sensible to moisture. The storage temperature is recommended by 25°C. Polyol should not be stored below 15°C and the isocyanate not below 20°C. The storage life is guaranteed for 3 months.
<b>Packaging and Supplying</b>	All products can be delivered in bulk, IBC and drum
<b>Changing</b>	-----
<b>First edition</b>	01-2017

The product information are made to the best of our believe, they are however not obligatory. This concerns also to trade mark rights of third parties. The above mentioned product information have to be proved additionally by an individual test of our products regarding the application for the intended processing of our purpose. The processing of our products and the products manufactured by the customer according to our technical support are out of our controlling possibilities and therefore subjects to the responsibility of the customer.